

CRACK FILLER

Pourable Sealer

Form: Thick Liquid

Color: Black

Odor: Solvent

pH: N/D

Solubility (in water): Soluble
(in mineral spirits): Insoluble

VOC Content (% by weight): N/D

Flash Point (ASTM D-7821): N/D

Specific Gravity: 1.02 g/cm³

Density: 8.51 lbs / gal

Storage Stability (at 70°F): 1 year

Ingredients

C.A.S.

Petroleum Asphalt.....	8052-42-4
Hydrous Aluminum Silicate.....	1332-58-79
Quartz.....	14808-60-7
Viscosity Modifier.....	7778-18-9
Biocide.....	55406-53-6

DIRECTIONS: Remove all dirt, gravel and foreign matter from cracks by sweeping or compressed air. Stir thoroughly and apply to cracks with suitable pouring can with spout. Use care to fill cracks completely without spreading excess material on pavement. CRACK FILLER may be leveled with squeegee. For cracks ½” or larger, mix 10 pounds of dry mason sand in 5 gallons CRACK FILLER with enough water to make a pourable slurry. Wash tools with detergent and water immediately after use.

CRACK FILLER is ideal for sealing potholes before filling with ALL WEATHER PATCH. Just spread in clean pothole and then fill with patch according to directions. Tracking problems and tackiness may be completely eliminated by sprinkling surface of CRACK FILLER with sand.

Do not apply if rain threatens within 24 hours or if temperature is expected to fall below 50°F. Allow 24 hours drying time before opening filled area to traffic. Do not use for sealing asphalt surface. KEEP FROM FREEZING.

Use on...
• Driveways
• Sidewalks
• Parking Lots
• Ensure your customers’ safety by eliminating the possibility of tripping over cracks in parking lots.

HMIS				NFPA		
Health.....	2	Severe	4	Extreme	Health.....	2
Flammability.....	1	Serious	3	High	Flammability.....	1
Reactivity.....	0	Moderate	2	Moderate	Reactivity.....	0
Personal Protection.....	None	Slight	1	Slight	Special Precautions.....	None
		Minimal	0	Insignificant		