

HANG ON

Do All Patching Mortar

Form: Powder

Color: Gray to gray-brown

Odor: None

pH: N/A

Solubility (in water): Slight
(in mineral spirits): Insoluble

VOC Content (% by weight): None

Flash Point (ASTM D-7821): None

Specific Gravity: 2.6 - 3.2 g/cm³

Density: 21.7 - 26.7 lbs/gal

Storage Stability (at 70°F): Stable

Ingredients

C.A.S. #

Silica Sand, Crystalline..... 14808-60-7
 Portland Cement..... 65997-15-1
 Amorphous Silica..... 7631-86-9
 Calcium Sulfate..... 10101-41-4 or 13397-24-5

Ideal for use on...

- **Concrete**
- **Masonry**
- **Mortar**
- **Stucco**
- **Horizontal / Vertical Surfaces**
- **Overhead Applications**
- **Almost All Tough Repair Jobs**

DIRECTIONS: Apply material above 40°F. Rub or scratch mixed material onto surface just prior to application. Do not allow rub or scratch coat to dry before applications. Check moisture content (mat test) prior to applying waterproof topping. Do not retemper already mixed material. Reasonable variations for the above data can be expected depending on field conditions, surface preparation, curing, contractor expertise and evaluation and/or handling of test cylinders. **Mixing guidelines:** Approximately 3 -4 quarts of water is required to mix 50 lb of product for patching applications. Always add and mix product into water. For applications 1.5” to 2” or more, extend product up to 40% with clean and dry 3/8” pea gravel.

HMIS				NFPA		
Health	2	Severe	4	Extreme	Health.....	2
Flammability.....	0	Serious	3	High	Flammability.....	0
Reactivity.....	1	Moderate	2	Moderate	Reactivity.....	1
Personal Protection.....	X	Slight	1	Slight	Special Precautions.....	None
		Minimal	0	Insignificant		